Laminex

Technical Data Sheet



Compact Laminate Alfresco

Summary

Laminex Compact Laminate - Alfresco with Protec+™ antimicrobial surface performance, is an exterior grade decorative panel manufactured under high pressure and temperature with UV inhibitors. The distinctive black core eliminates the need for edge treatment. Panels are durable for use in Alfresco applications.

Applications

• Benchtops • Furniture

Partitions

• Store Fixtures

- Decorative Wall Panelling
- Table Tops
- Alfresco Cabinetry

Functional Benefits















Horizontal Application

Stain Application Resistant

Resistant

Resistant

Scratch Resistant

Covered Outdoor

Antimicrobial

Product Characteristics

Vertical

| Attribute | Description |
|------------------------|---|
| Product Category | Compact Laminate |
| Substrate Type | Black Core |
| Sheet Size | 3600x 1500mm |
| Thickness (nominal) | 13mm |
| Weight (Kg/m2 approx.) | 18.5 |
| Decorative Surfaces | Double Sided (D/S) |
| Finish | Carbide |
| Colour/Pattern/Size | To view the full range, please visit www.laminex.com.au for the National Availability Guide |

Dimensional Tolerance (Tested to EN 438-4)

| Attribute | Description | |
|------------------------|---|--|
| Thickness | 12.0 ≤ t < 16.0 mm ± 0.60 mm | |
| Length and Width | 10mm/-0mm | |
| Flatness | 10.0 < t : 3,0 mm/m maximum deviation | |
| Straightness of edges* | ss of edges* 1.5 mm/m maximum deviation | |
| Squareness* | 1.5 mm/m maximum deviation | |

Provided the laminates are stored in the manner and conditions recommended by the manufacturer, they shall comply with the flatness requirements specified in the above table when # measured in accordance with EN 438-2, Clause 9. The flatness values specified in the above table apply to laminates with two decorative faces. Limits for laminates with one face sanded shall be agreed between supplier and customer.

Tolerances for cut-to-size panels shall be agreed between supplier and customer.





Technical Data Sheet Compact Laminate

hinate Alfresco

Surface Quality (Tested to EN438-2:2005)

| Attribute | Minimum Values |
|-------------------------------|--|
| | Viewing distance 0.75 to 1.5m from laminate surface |
| Inspection Guidelines | Light intensity approximately 800 to 1000 lx at the laminate surface |
| | Using normal vision, corrected if necessary. No magnification devices |
| Dirt, Spots & Similar Surface | The admissible size of defects is based on a maximum contamination area equivalent to $1.0 \text{ mm}^2/\text{m}^2$ and is proportional to the sheet size under inspection |
| Defects | The total admissible area of contamination may be concentrated in one spot or dispersed over an unlimited amount of smaller defects |
| Fibras Unios & Countrol os | The admissible size of defects is based on a maximum contamination length equivalent to 10mm/m ² and is proportional to the sheet size under inspection |
| Fibres, Hairs & Scratches | The total admissible length of contamination may be concentrated in one defect or dispersed over an unlimited amount of smaller defects |

Surface Performance (Tested to EN 438-2)

| Attribute | | Minimum Values |
|-----------------|--------------------|--|
| - | Surface Wear | Initial wear ≥ 150 cycle |
| | Immersion in | Average wear ≥ 350 cycles ≥ 2% |
| | Boiling Water | Slight change of gloss and/or colour, only visible at certain viewing angles |
| | Water Vapour | Appearance rating not worse than 4 |
| Resistance to | | Slight change of gloss and/or colour, only visible at certain viewing angles |
| Resistance to | Wet Heat at | Appearance rating not worse than 4 |
| | 100°C | Slight change of gloss and/or colour, only visible at certain viewing angles |
| | Dry Heat at | Appearance rating not worse than 4 |
| | 160°C | Slight change of gloss and/or colour, only visible at certain viewing angles |
| | cracking under | Appearance rating not worse than 4 |
| | stress/crazing | Hairline cracks only visible under 6X magnification |
| Dimensional sta | bility at elevated | Longitudinal direction: Maximum cumulative change 0.30 % |
| temperature | | Transverse direction: Maximum cumulative change 0.60 % |
| Lightfastness | | Contrast: Grey scale rating ≥ 4 |
| | | When tested in contrast with Blue wool 6 Ref: ISO 105-A02 |

Specialty Performance - Weather Resistance Properties

| Property | Test Method (EN438-2 Clause No.) | Property or Attribute | Unit (Max. or Min.) | Laminate Grade EDS and EDF |
|------------------------------|---|----------------------------|------------------------|--------------------------------------|
| | | Appearance | Rating (min) | 4 |
| Resistance to Climatic Shock | 19 | Flexural strength index Ds | (min) | 0.95 |
| | | Flexural modulus index Ds | (min) | 0.95 |
| | | Contrast | Grey scale rating | 3(after 1500 hours exposure) |
| Resistance to UV Light | 28 | | (not worse than) | |
| | | Appearance | Rating (min) | 4 (after 1500 hours exposure) |
| Resistance to artificial | | Contrast | Grey scale rating | 3 (after 650 MJ/m² radiant exposure) |
| weathering (including light | 29 | | (not worse than) | |
| fastness) | | Appearance | Rating (min) | 4 (after 650 MJ/m² radiant exposure) |

Rating 3 Hairline surface cracks and/or erosion of surface. Rating 4 Change of gloss only





Technical Data Sheet Compact Laminate Alfresco



Emissions & Environmental Performance

| Attribute | Tested to | Unit | Minimum Values |
|--------------|-------------|--------|----------------|
| Formaldehyde | ISO 12460-3 | mg/m²h | ≤ 3.5 |

Fire Properties (Typical Values)

| Attribute | Tested to | Unit | Requirement |
|--|---------------|-------|-------------|
| Fire hazard indices | AS/NZS 1530.3 | | 13mm |
| Ignitability | | index | 9 |
| Spread of flame | | index | 9 |
| Heat Evolved | | index | 6 |
| Smoke Developed | | index | 4 |
| Cone Calorimeter | AS/NZS 3837 | | |
| Group number | | | 3 |
| Average specific extinction area -13mm | | m²/kg | 97.4 |
| Average specific extinction area – 6mm | | m²/kg | 61.9 |
| Average heat release rate-13mm | | Kw/m² | 104 |
| Average heat release rate – 6mm | | Kw/m² | 107 |

Physical Properties

| Attribute | Tested to | Unit | Requirement |
|--------------------------------------|---------------|--------------------|-------------|
| Modulus of elasticity | EN ISO 178 | MPa | ≥ 9000 |
| Tensile strength | EN ISO 527-2 | MPa | ≥ 60 |
| Flexural strength | EN ISO 178 | MPa | ≥ 80 |
| Wear resistance | EN 438-2:10 | Cycles initial | 150 |
| wear resistance | LIN 430-2.10 | Cycles wear value | 350 |
| Steam resistance | EN 438-2:14 | Rating Gloss/Other | 3/4 |
| Dry heat at 160°C | EN 438-2:16 | Rating Gloss/Other | 3/4 |
| Stability at elevated temperature MD | EN 438-2:17 | % | 0.3 max |
| Stability at elevated temperature CD | EN 438-2:17 | % | 0.6 max |
| Impact resistance 13mm | EN 438-2:21 | mm | 1800 |
| Crazing resistance | EN 438-2:24 | Rating | 4 |
| Scratch resistance | EN 438-2:25 | Textured | 2N |
| Staining resistance | EN 438-2:26 | Rating Group 1 & 2 | 5 |
| Staining resistance | EN 438-2:26 | Rating Group 3 | 4 |
| Light fastness (xenon arc) | EN 438-2:27 | Grey scale | 4 to 5 |
| Cigarette burn resistance | EN 438-2:30 | Rating | 3 min |
| Wet heat resistance at 100°C | EN 12721:1997 | Rating Gloss/Other | 3/4 |



Laminex

Technical Data Sheet Compact Laminate

Alfresco



Staining Agents & Groups (Tested to EN 438-4)

| Attribute | Staining Agent | | Test Conditions | Contact Tim |
|--------------------|--|---|---------------------------------|-------------|
| Group 1 | Other organic solvents | Salt (NaCl) solutions | Apply staining | 16 hours |
| *Acetone | Toothpaste | Mustard | agent at ambient temperature | |
| | Hand cream | Lyes, soap solutions | | |
| | Urine | Cleaning solution consiting of: | | |
| | Alcoholic beverages | • 23% dodecylbenzene sulfonate | | |
| | Natural fruit and vegetable juices | • 10% alkyl aryl polyglycol ether | | |
| | Lemonade and fruit juices | • 67% water | | |
| | Meats and sausages | Commercial disinfectants | | |
| | Animal and vegetable fats and oils Water | Stain or paint removers based on organic solvents | | |
| | Yeast suspension in water | Citric Acid (10% solution) | | |
| Group 2 | Coffee (120g of coffee per litre of water) | Black (9g of tea per litre of water) | Apply staining agent | 16 hours |
| *Coffee | | Milk (all types) | at approximately 80°C | |
| | Wine vinegar | Nail varnish remover | Apply staining | 16 hours |
| | Alkaline-based cleaning agents (to 10% | Lipstick | agent at ambient temperature | |
| | concentration with water) | Water colours | | |
| | Hydrogen peroxide (3% solution) | Laundry marking links | | |
| | Ammonia (10% solution of commercial concentrate) | Ball point inks | | |
| | Nail varnish | | | |
| Group 31 | *Sodium hydroxide (25% solution) | *Shoe polish | Apply staining | 10 minutes |
| *Sodium hydroxide | *Hydrogen peroxide (30% solution) | Hair colouring and bleaching | agent at ambient temperature | |
| *Hydrogen peroxide | Concentrated vinegar (30% acetic acid) | agents | | |
| *Shoe polish | Bleaching agents and sanitary cleaners containing them | lodine Boric acid | | |
| | Hydrochloric acid based cleaning agents (≤ 3% HCl) | Lacquers and adhesives (except fast curing materials) | | |
| | Acid-based metal cleaners | Amidosulfonic acid descaling | | |
| | Mercurochrome (2,7-diabromo-4- hydroxymercurifluoresein, disodium salt) | agents (< 10% solution) | | |

1) Some commercial cleaning agents contain acids and alkalis in concentrations stronger than those shown in Group 3 and can cause surface marking or damage. Any spillage of such materials must be washed off immediately. Rating 5 Is equivalent to No visible change. Rating 4 is equivalent to Slight change of gloss and or colour, only visible at certain viewing angles. applications



Laminex Alfresco Compact with Protec+ contains antifungal and antibacterial resistant properties which do not wash off or leach out of the surface. It is safe for use in food preparation and processing activities and can be in direct contact with food, provided that good hygiene practices are followed.



Laminex

Technical Data Sheet Compact Laminate




Alfresco

Important Information

| Note | • | Details |
|------|---|---|
| W | ONLY use for internal/alfresco applications | Claims arising from non-internal applications are not covered under warranty |
| W | ONLY use compact laminate sheets within 12 months of purchase | Claims arising from sheets stored for longer than 12 months where storage/ environmental conditions cannot be maintained are not covered under warranty. |
| W | ALWAYS condition of panels prior to fabrication and installation | Claims attributable to failure to adhere to conditioning guidelines are not covered under warranty. |
| W | DO NOT bond directly to plaster, plasterboard, masonry or concrete | Claims arising from bonding to non-recommended surfaces resulting in undulations telegraphing to the decorative surface or poor bonding, are not covered under warranty |
| W | DO NOT use in installations where a Group 1 or 2 fire resistant product is required | |

(W) Denotes specific warranty conditions apply.

Laminex Compact Laminate Alfresco surfaces are not recommended for use in exterior applications where the product is exposed to direct sunlight outside the roof area, and its use in these applications will void the limited warranty (See Fig. 1). Direct roof area is that which is covered by the formal roofline of the property. Vergola or similar opening roof applications, acrylic sheeted roof products, sail &/or textile coverings are not considered a formal roof for this application. Colour change or fading due to UV exposure is not protected under warranty whether an interior or exterior application.



| Warranty Document | To view the latest Warranty Document for this product, please visit www.laminex.com.au. |
|-----------------------------|---|
| Care & Maintenance Document | To view the latest Care & Maintenance Document for this product, please visit www.laminex.com.au. |
| Safety Data Sheet | To view the latest Safety Data Sheet for this product, please visit www.laminex.com.au. |

