



NATA Accredited Laboratory

Accreditation No: 15305

Accredited for compliance with
ISO/IEC 17025 - Testing

Laminex[®]

a division of Laminex Group Pty Ltd ABN 98 004 093 092

The Laminex Group Technology Centre

Postal Address: PO BOX 720, Wendouree, Vic 3355

Address: 22 Trewin St, Wendouree, Vic 3355

Telephone: (03) 5337 3613

Fax: (03) 5337 3647

**Test Report No.
20PB-Whiteboard**

Date of Issue

19/08/2020

Client:

Laminex Australia

22 Trewin St

Wendouree

VIC 3355

This test report shall not be reproduced, except in full,
without written approval from The Laminex Group Technology Centre

The material contained in this report is confidential to the entity identified as 'Client' above.

As the sample(s) have been provided by the client, the results contained in this report apply only to the sample(s) as received.

Test Report No. 20PB-Whiteboard

Date of Issue: 19/08/2020

Laminex Sample Reference No.	25817
Client Sample Reference No.	786035
Product:	16mm Trade Essentials Whiteboard Moisture Resistant E1 Particleboard
Surface Treatment	Laminated both sides with white Low Pressure Melamine
Receive Date:	4/05/2020
Condition:	Good.
Testing Performed Date(s):	13-14/05/2020
Specification Standard	AS/NZS 1859.1:2017
Product Classification	>12 to 22mm MR E1 Particleboard

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.96	0.06	Maximum 1.5 (E1)	Clause 6.3 Table 1	PASS E1

Formaldehyde Emission Class: E1

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...



Test Report No. 20PB-Whiteboard

Date of Issue: 19/08/2020

Laminex Sample Reference No.	25624
Client Sample Reference No.	775862
Product:	18mm Trade Essentials Whiteboard Moisture Resistant E1 Particleboard
Surface Treatment	Laminated both sides with white Low Pressure Melamine
Receive Date:	10/03/2020
Condition:	Good.
Testing Performed Date(s):	17-19/03/2020
Specification Standard	AS/NZS 1859.1:2017
Product Classification	>12 to 22mm MR E1 Particleboard

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	1.07	0.05	Maximum 1.5 (E1)	Clause 6.3 Table 1	PASS E1

Formaldehyde Emission Class: E1

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...

