Laminex Decorwood®

Laminex Decorwood is a medium density fibreboard bonded on both sides with a hardwearing melamine decorative surface. Decorwood can be machined and face routed using conventional wood working tools.



APPLICATIONS

Decorwood® can be used in the following applications, in all areas away from high humidity, such as wall units, bedroom furniture, office furniture, wall lining, shelving.

Decorwood is offered in the lower formaldehyde emission level E0.

Note: Laminex Decorwood is for interior use only and should not be exposed to damp conditions or high humidity.

DECORATIVE SURFACE PROPERTIES

Decorwood, when tested in approved manner complies with the relevant sections of AS/NZS 1859.3 as per substrate properties table below:

RESISTANCE TO WEAR

AS/NZS 1859.3 requires minimum performance of:

Solid Colors

Average > 300 cycles.

Prints and Woodgrains

Average > 40 cycles.

SUBSTRATE PROPERTIES

(Typical physical properties when tested to AS/NZS 1859.2)					
		THICKNESS			
Specifications	Unit	5mm- 8mm	9mm- I2mm	13mm- 22mm	23mm- 33mm
Thickness Tolerance	mm	mm +/-0.2	mm +/-0.2	mm +/-0.3	mm +/-0.3
Density	kg/m³	780	760	730	720
Internal Bond	MPa	0.90	0.75	0.60	0.50
Modulus of Rapture	MPa	40.0	38.5	34.5	31.0
Modulus of Elasticity	MPa	3500	3600	3400	3400
Surface Soundness	MPa	0.6	0.9	1.2	1.4
Screw Holding, Face	Ν			800	800
Screw Holding, Edge	Ν			1000	1000
Thickness Swell (24hr)	%	<16	<10	<6	<6

^{*} Values reflect new testing methods for screw holding properties in AS/NZS 4266.13

WEIGHT

Thickness	9mm	I2mm	16mm	18mm	25mm	32mm
kg per m²	6.9	9.0	11.7	13.1	18.0	23.0

RESISTANCE TO STEAM

No noticeable permeability effects.

COLOURS

Decorwood comes in a limited range of colours from the Laminex Commercial Palette.

FINISH

Natural, Flint, Riven, Nuance.

Note: Finish options depend on colour. Check availability guide for finish options.

SHEET SIZES AND THICKNESSES

2400 x 1800mm 18, 25, 32mm

Section 5: 15.1

LOW PRESSURE LAMINATES

FIRE TESTS

(Typically achieved when tested to AS/NZS 1530.3)				
Indices	Result	Range		
Ignitability	14	0-20		
Spread of Flame	8	0-10		
Heat Evolved	7	0-10		
Smoke Developed	4	0-10		

Cone Calorimeter AS/NZS 3837					
(Irradiance of 50kW/m²)					
Classification	Result	Unit/Range			
Group Number	3	1-3			
Average Specific	53.3	m² / kg			
Extinction Area					

THIRD PARTY CERTIFICATION

Laminex Decorwood is an ecospecifier Global GreenTag™ GreenRate Level A certified product and can contribute to Green Star® points.



In addition, Laminex Decorwood has achieved Australian Forestry Standard / Programme for Endorsement of Forest Certification Schemes (AFS/PEFC) Chain of Custody (CoC). This ensures that the timber is sourced from sustainably managed forests and accrues Timber Credits in the Green Star Materials Calculator.





IMPORTANT NOTE

A slight variation exists between the finishes on Laminex melamine faced board products (Lamiwood MR, Decorwood, Vertiboard, Vertiboard MR, Structural and Contour Doors) and the Laminex high-pressure laminate products.

General Site Work Notes

Appendix 1. Handling & Product Application Guidelines Section 9:1

Laminate Product: Care & Maintenance

Appendix 2. General Care and Maintenance Section 9:2

Board Product: Site Work Notes

Appendix 3. Handling & Product Application Section 9:3

Board Product: Shelf Loadings

Appendix 3. Handling & Product Application Section 9:3

Greenfirst

Section 3:1

Section 5: 15.2

Issued October 2012